

Technical Data Sheet

PRODUCT DESCRIPTION:

Van Sickle Barn Paint is our premium quality latex coating, custom-designed for use on farm, ranch, and utility buildings, as well as fences. It is specifically formulated to provide high hiding, excellent color, and outstanding exterior durability. Van Sickle Barn Paint is extremely resistant to cracking, chipping, peeling, and blistering. Van Sickle Barn Paints are premixed and exceed the quality of most equally priced barn paints on the market.

TYPICAL USES:

Van Sickle Barn Paint can be used on all sound, properly prepared surfaces including wood, siding, trim, masonry, concrete block, asbestos shingles, and properly primed metal.

SURFACE PREPARATION:

Proper surface preparation is the most important variable in determining the service life of a coating. For best results, all surfaces must be clean, dry, and free from wax, oil, grease, dirt, mildew, loose rust, and any other contaminants. **NEW WOOD SURFACES:** prime with at least one coat of exterior latex or oil primer. **PREVIOUSLY PAINTED WOOD SURFACES:** remove all loose cracking and peeling paint, surface chalk, dust and dirt. Glossy surfaces should be lightly sanded. Prime bare spots with appropriate primer. After the surface has been properly prepared, apply two coats of Van Sickle Exterior Latex Barn Paint. **MASONRY:** must cure at least 60 days and be clean, free of dirt and sand. Old masonry must be thoroughly cleaned of peeling paint, loose sand, efflorescence, and mildew. Powdery or chalky surfaces must be cleaned and pre-dampened just before paint application. Apply two coats of Van Sickle Exterior Latex Barn Paint. **ASBESTOS SHINGLES:** should be weathered to a dull surface. Prime and apply two coats of Van Sickle Exterior Latex Barn Paint. **METAL:** prime bare metal with Van Sickle Equipment Enamel Primer. Two coats of primer are recommended and allow ample time to dry. Topcoat with one or two coats of Van Sickle Exterior Latex Barn Paint.

APPLICATION:

Apply by nylon or polyester brush, roller, or airless sprayer. Do not thin except for airless spray application, in which case you may thin up to 10% with clean water, if needed. May be applied to slightly damp surfaces. Do not mix with solvent paints, oils, thinners, or turpentine. Before and during application, stir the paint thoroughly from the bottom of the can with an upward motion, scraping the bottom to avoid pigment settling.

ENVIRONMENTAL VARIABLES:

Apply only when surface and air temperatures are between 50° and 90°F. Avoid painting late in the day when dew and condensation are likely to form or when rain is threatening. Avoid painting on hot

Product Codes & Colors

Gallon (71) 5-Gallon (75)

921 Flat Ranch Red

923 Flat Ranch White

951 Flat Forest Brown

Technical Data Sheet

ENVIRONMENTAL VARIABLES (continued)

days in direct sunlight. Cool, wet, humid, or over-applied coatings can greatly decrease a thorough cure and interfere with proper film formation. Always allow applied coat to dry before applying subsequent coats.

DRY-TIMES:

Drying time for this product will be approximately 1 hour to touch and may be recoated after 6 hours under ideal drying conditions.

CLEAN-UP:

Clean up all tools and equipment with warm, soapy water before paint dries.

CAUTIONS:

For exterior use only,
Do not take internally,
Use with adequate ventilation,

KEEP OUT OF REACH OF CHILDREN.

****WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.***

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Van Sickle Paint does not control the application of its products, or the condition of the surfaces to which they are applied, Van Sickle Paint's liability will under no circumstances exceed replacement of the product.

PHYSICAL PROPERTIES

Product Number	921, 923 & 951
General Type	Exterior Latex, Flat
Color	Various
Gloss	1 - 10 @ 60°
Solids By Weight	45.2%
Solids By Volume	29.2%
Theoretical Coverage @ 1 Mil DFT	468 Sq.Ft/Gal
Recommended DFT	2 - 2.5 mils
Viscosity @ 78°f	90-100 KU
Weight Per Gallon	10.7 - 10.8 lbs.
Flash Point	None
VOC (Maximum does not exceed)	100 g/L