

Product Data Sheet

PRODUCT DESCRIPTION:

Van Sickle® “rubberized” protective coating/bed liner is custom designed for use as a reasonably priced, do-it-yourself option to high cost spray-in bed liners. Rubber “crumb aggregate” is incorporated into a flexible, top quality resin system designed to give optimal performance for your investment.

TYPICAL USES:

Van Sickle Bedliner & Slip Resistant Coating can be used in a variety of applications where slip resistance or sound deadening qualities are desired. This product can be applied on properly prepared metal, fiberglass, wood, plywood, treated lumber, and concrete.

BASES & COLORS:

Black- Neutral Tint Base

PHYSICAL PROPERTIES:

PRODUCT NUMBER:	116
GENERAL TYPE:	Waterborne coating with rubber particles for texture
COLOR:	Black
GLOSS:	NA
SOLIDS BY WEIGHT:	53 %
SOLIDS BY VOLUME:	48 %
THEORETICAL COVERAGE @ 20+ MIL DFT:	30sq/ft
RECOMMENDED DFT:	20+ mils
VISCOSITY @ 78°F:	100-110
WEIGHT PER GALLON:	8.2 – 8.9 lbs.
FLASH POINT:	>200°F
EPA VOC:	0.5 lbs./ gallon

SURFACE PREPARATION:

For best results, all surfaces must be clean, dry, and free from wax, oil, grease, dirt, mildew, loose rust, and any other contaminants. New surfaces must be properly cleaned and primed with the appropriate primer. Previously painted surfaces must be removed or prepared to accept a new paint film. Glossy paint must be sanded or treated with a de-glossing solution so the new paint will adhere. Loose rust or paint, mill scale and contaminants must be removed by scraping, sanding, grinding or sandblasting. Feather sand rough edges, surface imperfections and prime uncoated surfaces with a recommended primer. Ferrous metal surfaces should be primed with Van Sickle Industrial Enamel Primer before any flash rust appears. Application of Van Sickle Industrial Enamel finish coat or primer is not recommended on coil coated or galvanized metal, masonry, aluminum or asbestos surfaces.

APPLICATION:

Apply by brush or short nap roller without thinning. Can be sprayed with a drywall texture gun at 7-10 PSI and 3/16 nozzle. Apply only when surface and air temperatures are between 50 and 90 degrees, for both application and cure. Stir frequently during use. Two coats are recommended to achieve adequate coating build up, and even distribution of the rubber aggregate.

ENVIRONMENTAL VARIABLES:

Apply only when surface and air temperatures are between 50° and 90°F. Avoid painting on hot days, in direct sunlight or late in the day when dew is likely to form. Cool, wet, humid or over-applied coatings can greatly increase through cure and interfere with proper film formation.

Dry-Times:

With proper film application and ideal drying conditions, an ideal dry time will be 4-6 hours to touch, and may be recoated after 9-12 hours. Light duty use after 12 hours, with maximum durability within 1-2 weeks. Please refrain from heavy duty use until the 2 week mark to ensure maximum performance.

CLEAN-UP: Clean up all tools and equipment with warm, soapy water before paint is allowed to dry.



Product Data Sheet

CAUTIONS:

For exterior use only,
Do not take internally,
Use with adequate ventilation,
KEEP OUT OF REACH OF CHILDREN

*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Van Sickle Paint does not control the application of its products, or the condition of the surfaces to which they are applied, Van Sickle Paint's liability will under no circumstances exceed replacement of the product.

