

870

Interior Latex Primer, Flat
White



Product Data Sheet

PRODUCT DESCRIPTION:

Van Sickle® Interior Latex Primer is designed to meet rigid performance requirements for service and durability. It is custom-built with quality pigments and latex resins to provide superior performance on all drywall construction. Specifically formulated to provide easy application, excellent adhesion and hiding. Van Sickle® Interior Latex Primer builds an ideal foundation for all latex finish coats. Van Sickle® Interior Latex Primer can be tinted to pastel or tint base colors with any universal tinting system.

TYPICAL USES:

Van Sickle® Interior Latex Primer can be used on wallboard or all types of composition boards. NOT RECOMMENDED for use on raw, painted or stained wood surfaces.

BASES & COLORS:

870 Interior Latex Primer, Flat White

PHYSICAL PROPERTIES:

PRODUCT NUMBER:	870
GENERAL TYPE:	Interior Latex Primer
COLOR:	White
GLOSS:	1-10 @ 60°
SOLIDS BY WEIGHT:	49.9%
SOLIDS BY VOLUME:	35.4%
THEORETICAL COVERAGE @ 1 MIL DFT:	564Sq.Ft/Gal
RECOMMENDED DFT:	1.5-2mils DFT
VISCOSITY @ 78°F:	90-95 KU
WEIGHT PER GALLON:	10.7-10.8 lbs.
FLASH POINT:	None
VOC:	114.0 G/L

SURFACE PREPARATION:

Proper surface preparation is the most important variable in determining the service life of any coating system. For best results the surface to be painted must be clean and dry, free of dirt, wax, oil, grease, dust and water-soluble material. Patch any nail holes, cracks or surface imperfections. Any glossy surfaces should be dulled by sanding and wiped free of dust.

APPLICATION:

Apply by polyester or nylon brush, roller or spray. Do not thin; use as is from the container. If thinning is necessary, thin up to 10% with clean water. Do not add solvent paints, varnishes or paint thinner to this product. Before and during application, stir the paint thoroughly from the bottom of the can with an upward motion, scraping the bottom to avoid pigment settling.

ENVIRONMENTAL VARIABLES:

Apply only when surface and air temperatures are between 50° and 90°F. Cool, wet, humid or over-applied coatings can greatly decrease a thorough cure and interfere with proper film formation. Always allow applied coat to dry before applying subsequent coats.

Dry-Times:

Drying time for this product will be approximately 1 hour to touch, and may be recoated after 6 hours under ideal drying conditions.

CLEAN-UP:

Clean up all tools and equipment with warm, soapy water before paint dries.



870

Interior Latex Primer, Flat
White



Product Data Sheet

CAUTIONS:

For interior use only,
Do not take internally,
Use with adequate ventilation,
KEEP OUT OF REACH OF CHILDREN

*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Van Sickle Paint does not control the application of its products, or the condition of the surfaces to which they are applied, Van Sickle Paint's liability will under no circumstances exceed replacement of the product.

