

## Product Data Sheet

### **PRODUCT DESCRIPTION:**

Van Sickle® Exterior Latex Primer is formulated to meet rigid performance requirements for durability and service. It is custom-built to provide a uniform base on new wood or badly weathered old siding. It is specifically designed to provide easy application, excellent adhesion, and superior resistance to weather, high hiding and excellent color. Use under latex finish coats. Van Sickle® Exterior Latex Primer can be tinted with any universal tinting system to match topcoat colors (in pastel or tint base colors).

### **TYPICAL USES:**

Van Sickle® Exterior Latex Primer can be used on all properly prepared surfaces of wood, siding and trim.

### **BASES & COLORS:**

922 Exterior Latex Primer, Flat White

### **PHYSICAL PROPERTIES:**

PRODUCT NUMBER:	922
GENERAL TYPE:	Exterior Latex Primer, Flat
COLOR:	White
GLOSS:	1-10 @ 60°
SOLIDS BY WEIGHT:	44.6%
SOLIDS BY VOLUME:	30.4%
THEORETICAL COVERAGE @ 1 MIL DFT:	487Sq.Ft/Gal
RECOMMENDED DFT:	1.5-2mils DFT
VISCOSITY @ 78°F:	90-95 KU
WEIGHT PER GALLON:	10.5-10.6 lbs.
FLASH POINT:	None
VOC:	139.0 G/L

### **SURFACE PREPARATION:**

Proper surface preparation is the most important variable in determining the service life of any coating system. For best results, all surfaces must be clean, dry and free from wax, oil, grease, dirt, mildew, loose rust, and any other contaminants. Chemical cleaning is preferred; however, other cleaning methods may be acceptable depending on condition and type of contaminant on surface. Old glossy paint films must be sanded or treated with a de-glossing solution so the new paint can adhere to the old. Scrape off all loose, cracking or peeling paint and make sure all imperfections are repaired.

### **APPLICATION:**

Apply by brush, roller or airless spray. Do not thin except for airless spray application, in which case you may thin with up to 10% clean water, if needed. May be applied to slightly damp surfaces. Do not mix with solvent paints, oils, thinners or turpentine. Before and during application, stir the paint thoroughly from the bottom of the can with an upward motion, scraping the bottom to avoid pigment settling.

### **ENVIRONMENTAL VARIABLES:**

Apply only when surface and air temperatures are between 50° and 90°F. Avoid painting late in the day when dew and condensation are likely to form or when rain is threatening. Avoid painting on hot days in direct sunlight. Cool, wet, humid or over-applied coatings can greatly decrease a thorough cure and interfere with proper film formation. Always allow applied coat to dry before applying subsequent coats.

### **Dry-Times:**

Drying time for this product will be approximately 1 hour to touch, and may be recoated after 6 hours under ideal drying conditions.

### **CLEAN-UP:**

Clean up all tools and equipment with warm, soapy water before paint dries.



**922**

Exterior Latex Primer, Flat  
White



## Product Data Sheet

---

### **CAUTIONS:**

For exterior use only,  
Do not take internally,  
Use with adequate ventilation,  
**KEEP OUT OF REACH OF CHILDREN**

\*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

### **Limited Warranty**

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Van Sickle Paint does not control the application of its products, or the condition of the surfaces to which they are applied, Van Sickle Paint's liability will under no circumstances exceed replacement of the product.

