

Product Data Sheet

PRODUCT DESCRIPTION:

Van Sickle Beehive Exterior Acrylic Latex is our finest quality latex built to meet the demands of protecting and maintaining hive boxes. Specifically formulated to provide excellent exterior durability and high hide, this product can be applied in temperatures as low as 35°F. It is made to be extremely resistant to cracking, chipping, peeling, and blistering. Easy application by brush, roll or spray, this long-lasting acrylic formula ensures that your beehive will be protected from weather and exposure to the elements.

TYPICAL USES:

Van Sickle Beehive Exterior Acrylic Latex is designed for use on all properly prepared surfaces of wood, siding, and many other surfaces.

BASES & COLORS:

939 Exterior White Acrylic Latex Beehive Paint

PHYSICAL PROPERTIES:

PRODUCT NUMBER:	939
GENERAL TYPE:	Exterior Latex Flat
COLOR:	White
GLOSS:	<5 @ 60°
SOLIDS BY WEIGHT:	48.94%
SOLIDS BY VOLUME:	31.92%
THEORETICAL COVERAGE @ 1 MIL DFT:	512 SF./Gal
RECOMMENDED DFT:	2 – 3 mils DFT
VISCOSITY @ 78°F:	100-102 KU
WEIGHT PER GALLON:	11.13 lbs.
FLASH POINT:	NONE
VOC:	<50 g/L

SURFACE PREPARATION:

Proper surface preparation is the most important variable in determining the service life of a coating. For best results, all surfaces must be clean, dry and free from wax, oil, grease, dirt, mildew, loose rust, and any other contaminants. **NEW WOOD SURFACES:** prime with at least one coat of exterior latex or oil primer. **PREVIOUSLY PAINTED WOOD SURFACES:** remove all loose cracking and peeling paint, surface chalk, dust and dirt. Glossy surfaces should be lightly sanded. Prime bare spots with appropriate primer. After surface has been properly prepared, apply two coats of Van Sickle Beehive Exterior Acrylic Latex. **MASONRY** must cure at least 60 days and be clean, free of dirt and sand. Old masonry must be thoroughly cleaned of peeling paint, loose sand, efflorescence and mildew. Powdery or chalky surfaces must be cleaned and pre-dampened just before paint application. Apply two coats of Van Sickle Beehive Exterior Acrylic Latex.

APPLICATION:

Apply by nylon or polyester brush, roller or airless spray. Do not thin except for airless spray application, in which case you may thin with up to 10% clean water, if needed. May be applied to slightly damp surfaces. Do not mix with solvent paints, oils, thinners or turpentine. Before and during application, stir the paint thoroughly from the bottom of the can with an upward motion, scraping the bottom to avoid pigment settling.

ENVIRONMENTAL VARIABLES:

Apply only when surface and air temperatures are maintained above 35° F and below 90° F. Avoid painting late in the day when dew and condensation are likely to form or when rain is threatening. Avoid painting on hot days in direct sunlight. Cool, wet, humid or over-applied coatings can greatly decrease a thorough cure and interfere with proper film formation. Always allow applied coat to dry before applying subsequent coats.

Dry-Times:

Drying time for this product will be approximately 1/2- 1 hour to touch, and may be recoated after 2-4 hours above 50° F and 24 hours at temperatures between 35° F and 49° F.

CLEAN-UP:

Clean up all tools and equipment with warm, soapy water before paint dries.



939

Van Sickle Beehive Exterior Acrylic
Latex Flat



Product Data Sheet

CAUTIONS:

For exterior use only,
Do not take internally,
Use with adequate ventilation,
KEEP OUT OF REACH OF CHILDREN

*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Van Sickle Paint does not control the application of its products, or the condition of the surfaces to which they are applied, Van Sickle Paint's liability will under no circumstances exceed replacement of the product.

